

THIN FILM TRANSISTOR AND MANUFACTURING METHOD THEREOF

BACKGROUND OF THE INVENTION

5 Field of the Invention

[0001] The present invention generally relates to a thin film transistor (TFT) and the manufacturing method thereof. More particularly, the present invention generally relates to a thin film transistor (TFT) having a material of channel layer which is composed of lightly doped amorphous silicon, and the manufacturing method thereof

10

Description of the Related Art

[0002] In recent years, a variety of macromedia electronic devices and products are drastically developed due to the rapid development of the semiconductor device and the user interface of the device. Conventionally, since the cathode ray tube (CRT) display device is low-cost and has high performance, it is widely used display device. However, as to the display device of the personal computer, the cathode ray tube (CRT) display has the disadvantages of large size and high power consumption. Accordingly, the liquid crystal display (LCD) being small, lightweight, use low operational voltage, low power consumption, radiation free and environmentally friendly, gradually replaced the conventional CRT display. In recent years, the liquid crystal display (LCD), for example, the thin film transistor (TFT) liquid crystal display (LCD) has become the main stream of the display devices.

20

[0003] In general, the conventional thin film transistor (TFT) may be classified into amorphous silicon thin film transistor (TFT) and polysilicon thin film transistor

(TFT). It is noted that, the technology of low temperature polysilicon (LTPS) is different from the technology of conventional amorphous silicon (α -Si). In the low temperature polysilicon (LTPS) technology, the electron mobility can be enhanced to more than 200cm²/V-sec. Therefore, the size of the thin film transistor (TFT) can be minimized, the aperture ratio of the display can be enhanced, and the power consumption can be reduced. However, because of the manufacturing process of the amorphous silicon thin film transistor (TFT) technology is well developed, simple and low-cost, the amorphous silicon thin film transistor (TFT) technology is still the main stream of the array of the display device.

[0004] FIG. 1 is a cross-sectional view schematically illustrating the structure of conventional amorphous silicon thin film transistor (TFT). Referring to FIG. 1, the thin film transistor (TFT) 100 includes a substrate 110, a gate 120, an inter-gate dielectric layer 130, a channel layer 140 and source/drain regions 150. The gate 120 is disposed on the substrate 110. The inter-gate dielectric layer 130 is disposed on the substrate and covers the gate 120. The channel layer 140 is disposed on a portion of the inter-gate dielectric layer 130 that at least covers the gate 120. The source/drain regions 150 are disposed on the channel layer 140 and are separated by a distance. When the gate 120 operates to supply an operating voltage to the channel layer 140, the source/drain regions 150 are electrically connected by the channel layer 140.

[0005] The manufacturing method of the channel layer 140 of the conventional thin film transistor (TFT) 100 includes the following steps. First, the substrate 110 is transported into a reaction chamber (not shown) and the substrate is subjected to a reaction gas mixture comprising of silane (SiH₄) and hydrogen (H₂) in the reaction

chamber to form an intrinsic amorphous silicon layer. Next, the amorphous silicon layer is patterned to form the channel layer 140.

[0006] Accordingly, because the channel layer of the thin film transistor (TFT) is an intrinsic amorphous silicon layer, the electron mobility and the turning-on-current are not high enough when the thin film transistor is operated.

SUMMARY OF THE INVENTION

[0007] Accordingly, one object of the present invention is to provide a thin film transistor (TFT) and the manufacturing method thereof to increase the turning-on-current and the electron mobility of the channel region of the thin film transistor (TFT).

[0008] In accordance with the above objects and other advantages of the present invention, a manufacturing method of thin film transistor (TFT) is provided. The manufacturing method includes the following steps. First, a gate is formed on a substrate. Next, an inter-gate dielectric layer is formed over the substrate covering the gate. Next, a channel layer is formed covering on a portion of the inter-gate dielectric layer at least covering the gate. The channel layer comprises a lightly doped amorphous silicon layer. Next, source/drain regions are formed on the channel layer, wherein the source/drain regions are separated by a distance.

[0009] In an embodiment of the present invention, the channel layer comprises an N-type lightly doped amorphous silicon layer. In another embodiment of the invention, the channel layer may comprises a P-type lightly doped amorphous silicon layer.

[0010] In an embodiment of the present invention, the channel layer, for example but not limited to, doped with phosphorous atoms, and a concentration of

phosphorous atoms in the channel layer is in a range of about $1\text{E}17\text{atom}/\text{cm}^3$ to about $1\text{E}18\text{atom}/\text{cm}^3$. In another embodiment of the invention, the channel layer is, for example but not limited to, doped with boron atoms, and a concentration of boron atoms in the channel layer is in a range of about $1\text{E}16\text{atom}/\text{cm}^3$ to about $5\text{E}17\text{atom}/\text{cm}^3$.

5 **[0011]** In an embodiment of the present invention, the channel layer is formed by performing, for example but not limited to, a chemical vapor deposition (CVD) process using a reaction gas mixture comprising silane (SiH_4), hydrogen and phosphine (PH_3), wherein a flow ratio of phosphine (PH_3) is in a range of about 0.28ppm to about 8ppm, wherein the flow ratio of the phosphine (PH_3) is equal to the ratio of the flow of
10 phosphine (PH_3) to the total flow of silane (SiH_4), hydrogen and phosphine (PH_3).

[0012] In another embodiment of the present invention, the channel layer is formed by performing, for example but not limited to, a chemical vapor deposition (CVD) process using a reaction gas mixture comprising silane (SiH_4), hydrogen and boroethane (B_2H_6), wherein a flow ratio of the boroethane (B_2H_6) is in a range of about
15 0.5ppm to about 10ppm, and wherein the flow ratio of the boroethane (B_2H_6) is equal to the ratio of the flow of boroethane (B_2H_6) to the total flow of silane (SiH_4), hydrogen and boroethane (B_2H_6).

[0013] In an embodiment of the present invention, the channel layer is formed by, for example but not limited to, forming a first lightly doped amorphous silicon layer
20 on a portion of the inter-gate dielectric layer at a first deposition rate, and forming a second lightly doped amorphous silicon layer on the first lightly doped amorphous silicon layer at a second deposition rate, wherein the first deposition rate is lower than the second deposition rate.

[0014] In an embodiment of the present invention, the method further includes, for example but not limited to, a step of forming an ohmic contact layer on the channel layer between the steps of forming the channel layer and the step of forming the source/drain regions.

5 [0015] In an embodiment of the present invention, the method further includes, for example but not limited to, a step of forming a protection layer on the substrate covering the source/drain regions, the channel layer and the inter-gate dielectric layer.

[0016] In accordance with above objects and other advantages of the present invention, a thin film transistor (TFT) is provided. The thin film transistor (TFT)
10 includes a substrate, a gate, an inter-gate dielectric layer, a channel layer and source/drain regions. The gate is disposed on the substrate, and the inter-gate dielectric layer is disposed on the substrate and covers the gate. The channel layer is disposed over a portion of the inter-gate dielectric layer, wherein the channel covers the gate. The channel layer comprises a lightly doped amorphous silicon layer. The
15 source/drain regions are disposed over the channel layer, wherein the source/drain regions are separated by a distance.

[0017] In an embodiment of the present invention, the channel layer comprises an N-type lightly doped amorphous silicon layer. In another embodiment of the invention, the channel layer may comprises a P-type lightly doped amorphous silicon
20 layer.

[0018] In an embodiment of the present invention, the channel layer is, for example but not limited to, doped with phosphorous atoms, and a concentration of phosphorous atoms in the channel layer is in a range of about $1\text{E}17\text{atom}/\text{cm}^3$ to about $1\text{E}18\text{atom}/\text{cm}^3$. In another embodiment of the invention, the channel layer is, for

example but not limited to, doped with boron atoms, and a concentration of boron atoms in the channel layer is in a range of about $1 \times 10^{16} \text{ atom/cm}^3$ to about $5 \times 10^{17} \text{ atom/cm}^3$.

5 **[0019]** In an embodiment of the present invention, the method of forming the channel layer includes, for example but not limited to, forming a first lightly doped amorphous silicon layer on a portion of the inter-gate dielectric layer, and then forming a second lightly doped amorphous silicon layer on the first lightly doped amorphous silicon layer.

10 **[0020]** In an embodiment of the present invention, the TFT further includes, for example but not limited to, an ohmic contact layer disposed between the channel layer and the source/drain.

[0021] In an embodiment of the present invention, the TFT further includes, for example but not limited to, a protection layer disposed on the substrate covering the source/drain regions, the channel layer and the inter-gate dielectric layer.

15 **[0022]** According to an aspect of the present invention, a lightly doped amorphous silicon layer is provided as a channel layer achieve at least the advantages of increased electron mobility of the channel layer and thereby increase the turning-on-current of thin film transistor (TFT) without increasing the leakage current, and the improvement of the ohmic contact between the channel layer and the source/drain regions.

20 **[0023]** It is to be understood that both the foregoing general description and the following detailed description are exemplary, and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0024] The accompanying drawings are included to provide a further understanding of the invention, and are incorporated in and constitute a part of this specification. The following drawings illustrate embodiments of the invention and, together with the description, serve to explain the principles of the invention.

[0025] FIG. 1 is a cross-sectional view schematically illustrating the structure of a conventional amorphous silicon thin film transistor (TFT).

[0026] FIG. 2A to FIG. 2F are cross-sectional views schematically illustrating the process flow of a process of forming a thin film transistor (TFT) according to a preferred embodiment of the present invention.

[0027] FIG. 3 is a plot illustrating the relationship between the turning-on-current and the flow ratio of the phosphine (PH_3) in the process of forming the thin film transistor (TFT) according to one of the preferred embodiment of the present invention.

[0028] FIG. 4 is a plot illustrating the relationship between the electron mobility and the flow ratio of the phosphine (PH_3) in the process of forming the thin film transistor (TFT) according to one of the preferred embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0029] The present invention now will be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will be thorough and complete,

and will fully convey the scope of the invention to those skilled in the art. Like numbers refer to like elements throughout.

[0030] FIG. 2A to FIG. 2F are cross-sectional views schematically illustrating the process flow of a process of forming a thin film transistor (TFT) according to a preferred embodiment of the present invention. As shown in FIG. 2A, a gate 220 is formed over a substrate 210. Next, an inter-gate dielectric layer 230 is formed over the substrate 210 at least covering the gate 220. The method of forming the gate 220 includes, for example but not limited to, forming a first conductive layer (Metal 1) over the substrate 210 by performing a sputtering process, and then performing well known photolithography and etching process to form the gate 220. The inter-gate dielectric layer 230 can be formed by, for example but not limited to, performing a plasma enhance chemical vapor deposition (PECVD) process.

[0031] Furthermore, the substrate 210 includes, for example but not limited to, a glass substrate, a transparent plastic substrate or a substrate composed of any transparent material. The material of the gate 220 includes, for example but not limited to, tantalum (Ta), chromium (Cr), molybdenum (Mo), titanium (Ti) or aluminum (Al) or other conductive material. The material of the inter-gate dielectric layer 230 includes, for example but not limited to silicon nitride (SixNy), silicon oxynitride (SiON), silicon oxide (SiOx) or other dielectric material.

[0032] Next, as shown in FIG. 2B, a channel layer 240 is formed on a portion of the inter-gate dielectric layer 230 at least covering the gate 220. The channel layer 240 comprises, for example but not limited to, lightly doped amorphous silicon layer, wherein the doped amorphous silicon layer comprises an N-type lightly doped amorphous silicon layer or P-type lightly doped amorphous silicon layer. The channel

layer 240 can be formed by performing, for example but not limited to, a chemical vapor deposition (CVD) process. The CVD process includes, for example, transporting the substrate 210 into a reaction chamber (not shown). Next, a reaction gas mixture is charged into the reaction chamber, wherein the reaction gas mixture comprises, for example but not limited, silane (SiH_4), hydrogen (H_2) and phosphine (PH_3). Alternatively, the reaction gas mixture may comprise silane (SiH_4), hydrogen (H_2) and boroethane (B_2H_6). For the reaction gas comprising phosphine (PH_3), the flow ratio of the phosphine (PH_3) is, for example but not limited to, in a range of about 0.28ppm to about 8ppm. And, for the reaction gas comprising boroethane (B_2H_6), the flow ratio of the boroethane (B_2H_6) is, for example but not limited to, in a range of about 0.5ppm to about 10ppm. The flow ratio of the phosphine (PH_3) is equal to the ratio of the flow of phosphine (PH_3) to the total flow of silane (SiH_4), hydrogen and phosphine (PH_3). The flow ratio of the boroethane (B_2H_6) is equal to the ratio of the flow of boroethane (B_2H_6) to the total flow of silane (SiH_4), hydrogen and boroethane (B_2H_6).

[0033] In an embodiment of the present invention, the channel layer 240 is, for example but not limited to, doped with phosphorous atoms. The concentration of phosphorous atoms is, for example but not limited to, in a range of about $1\text{E}17\text{atom}/\text{cm}^3$ to $1\text{E}18\text{atom}/\text{cm}^3$. Alternatively, the channel layer 240 is, for example but not limited to, doped with boron atoms. The concentration of boron atoms is, for example but not limited to, in a range of about $1\text{E}16\text{atom}/\text{cm}^3$ to $5\text{E}17\text{atom}/\text{cm}^3$.

[0034] The method of forming the channel layer 240 is described as follows. First, a first lightly doped amorphous silicon layer 242 is formed over a portion of the inter-gate dielectric layer 230 at least covering the gate 220 at a first deposition rate.

Next, a second lightly doped amorphous silicon layer 244 is formed over the first lightly doped amorphous silicon 242 at a second deposition rate. In an embodiment of the invention, the first deposition rate is, lower than the second deposition rate.

5 [0035] Next, as shown in FIG. 2C, an ohmic contact layer 250 is formed over the channel layer 240, wherein the ohmic contact layer 250 has an excellent contact with a metal surface. The method of forming the ohmic contact layer 250 includes, for example but not limited to, performing an ion implant process to implant N-type ions into the amorphous silicon layer.

10 [0036] Next, as shown in FIG. 2D, source/drain region 260 are formed over the channel layer 240. The forming method of source/drain regions 260 includes, for example but not limited to, first forming a second conductive layer (Metal 2) over the substrate 210, and then performing the well known photolithography and etching process to form the source/drain regions 260. The material of the source/drain 260 includes, for example but not limited to, tantalum (Ta), chromium (Cr), molybdenum
15 (Mo), titanium (Ti), aluminum (Al), or other conductive material.

[0037] Next, as shown in FIG. 2E, a protection layer 270 is formed over the substrate 210 to cover the source/drain regions 260, the channel layer 240 and the inter-gate dielectric layer 230. The protection layer 270 comprises an opening 272 exposing a portion of the source/drain region 260 there-within.

20 [0038] Next, as shown in FIG. 2F, a transparent conductive layer 280 is formed over the protection layer 270 and electrically connected to the source/drain region 260 through the opening 272. The transparent conductive layer 280 includes, for example but not limited to, a pixel electrode. The material of the transparent conductive layer

280 includes, for example but not limited to, indium tin oxide (ITO), strontium tin oxide (STO), or other transparent conductive material.

[0039] Referring to FIG. 2E, a structure of the thin film transistor (TFT) 200 of the present invention is shown. The TFT comprises a substrate 210, a gate 220, an inter-gate dielectric layer 230, a channel layer 240 and source/drain regions 260. The gate 220 is disposed over the substrate 210. The inter-gate dielectric layer 230 is disposed over the substrate 210 and covers the gate 220. The channel layer 240 is disposed on a portion of the inter-gate dielectric layer 230 at least covering the gate 210. The material of the channel layer 240 includes, for example, a lightly doped amorphous silicon layer. The source/drain regions 260 are disposed over the channel layer 240, wherein the source/drain are separated by a distance.

[0040] Furthermore, the channel layer 240 comprises, for example but not limited to, an N-type lightly doped amorphous silicon layer or P-type lightly doped amorphous silicon layer.

[0041] Furthermore, the channel layer 240 is, for example but not limited to, doped with phosphorous atoms, and the concentration of phosphorous atoms in the channel layer 240 is, for example but not limited to, in a range of about $1\text{E}17\text{atom}/\text{cm}^3$ to about $1\text{E}18\text{atom}/\text{cm}^3$. Alternatively, the channel layer 240 is, for example but not limited to, boron atoms, and the concentration of boron atoms in the channel layer 240 is, for example but not limited to, in a range of about $1\text{E}16\text{atom}/\text{cm}^3$ to about $5\text{E}17\text{atom}/\text{cm}^3$.

[0042] Moreover, the channel layer 240 can be formed by, for example but not limited to, sequentially forming a first lightly doped amorphous silicon layer 242 and a second lightly doped amorphous silicon layer 244 over the inter-gate dielectric layer

220. The first lightly doped amorphous silicon layer 242 is disposed, for example but not limited to, on a portion of the inter-gate dielectric layer 220 that at least covers the gate 210. The second lightly doped amorphous silicon layer 244 is disposed, for example but not limited to, on the first lightly doped amorphous silicon layer 242.

5 **[0043]** Moreover, the thin film transistor (TFT) 210 further includes, for example but not limited to, an ohmic contact layer 250 and a protection layer 270 formed over the substrate 210. The ohmic contact layer 250 is disposed, for example but not limited to, between the channel layer 240 and the source/drain regions 260 to enhance the ohmic contact the channel layer 240 and the source/drain regions 260.

10 The protection layer 270 is disposed on, for example but not limited to, the substrate 210, and the protection layer 270 covers the source/drain regions 260, the channel layer 240 and the inter-gate dielectric layer 220.

[0044] However, it is noted that, the above-described thin film transistor (TFT) and the manufacturing method thereof of the embodiments of the present invention is provided as exemplary embodiments of the invention. Further, the use of channel

15 layer composed of lightly doped amorphous silicon layer in a thin film transistor (TFT) and the process of forming the same in a TFT falls within the scope of the present invention.

[0045] FIG. 3 is a plot illustrating the relationship between the turning-on-

20 current and the flow ratio of phosphine (PH_3) in the process of forming the thin film transistor (TFT) according to one of the preferred embodiment of the present invention. FIG. 4 is a plot illustrating the relationship between the electron mobility and the flow ratio of phosphine (PH_3) in the process of forming the thin film transistor (TFT) according to one of the preferred embodiment of the present invention. As shown in

FIG. 3, the turning-on-current of the thin film transistor (TFT) increases drastically with the increasing flow ratio of the phosphine (PH_3) in presence of the channel layer. As shown in FIG. 4, the electron mobility of the channel layer of the thin film transistor (TFT) drastically increases with the increasing flow ratio of the phosphine (PH_3) in
5 presence of the channel layer.

[0046] Furthermore, the TFT of the present invention was tested, the test results reveal that the TFT of the present invention do not have excess the leakage current, and the ohmic contact between the channel layer and the source/drain is substantially improved.

10 **[0047]** It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present invention without departing from the scope or spirit of the invention. In view of the foregoing, it is intended that the present invention cover modifications and variations of this invention provided they fall within the scope of the following claims and their equivalents.